Advanced Photon Source
Experimental Facilities Division,
Argonne National Laboratory, 9700 South Cass Avenue, Illinois 60439

Report on Optical Substrate Measurements

Date: 05/17/05	Reference #: M05075A	Page # 1/3	
Component: Flat KB mirror Manufacturer:	Requester: E. Dufresne Affiliation: MHATT-CAT Beamline: 07-ID	Date in/out: May 16, 05/May 17, 05	
Lab coordinator: L. Assoufid	Measurement by: J. Qian	Report by: J. Qian	

	Tizensurement of the grant		Postojivi	Z
Description of the measured com	ponent:			
Flat KB mirror:				
Size: 23.8 – 46 mm x 200 r	mm x 7 mm			
Coating: No				
Performed measurements:				
Surface roughness (Determ	ine which side of the KB mi	rror is super	-polished)	
Surface slope (Measure the	e super-polished surface only	y)		
Instruments used for measuring				
An "X" indicates the instrument(s)	used.			
Surface roughness:	WYKO-TOPO-2D,	1.5x	X 5x	40x
	WYKO-TOPO-3D,	1.5x	5x	40x
Surface figure:	WYKO-6000			
Surface slope:	X LTP			

Report on Optical Substrate Measurements

Date: 5/17/05 Reference #: M05075A Page # 2/3

Surface roughness measurement with the TOPO2D, objective 5X

- The separation of adjacent measured spots was about 10 mm.

- Table 1 summarizes the roughness measurement results of the mirror.

Table 1. Results of the roughness measurements. (Profile length: 2.66 mm)

Surface	Meas. (#)	RMS (A°)	P-V (A°)	Radius (km)
Super-polished (marked with an arrow on side of the mirror)	tivi 1 cen	1.06	6.3	-1.0
	2	0.80	4.7	-0.8
	3	0.71	4.3	-1.0
	4	0.93	5.0	-0.9
	5	0.84	4.9	-1.0
	Mean	0.87	5.0	
The other side	1	9.2	51.3	-0.9
	2	8.2	38.9	-2.2
	Mean	8.7	45.1	

Surface slope profile measurement with the LTP

- The mirror was set face-up and scanned over a length of central 172 mm (see Figure 1).
- Table 2 summarizes the results of the LTP measurements. Residual slope data were obtained by removing the best-fit cylinder from the LTP raw profiles.
- Figure 2 shows the residual slope and height profiles.




Figure 1. LTP scan direction.

Report on Optical Substrate Measurements

Date: 5/17/05 Reference #: M05075A Page # 3/3

Table 2. Results of the surface slope measurements.

Residu	al slope	Residua	Residual height Radius (km)		Figure (#)
RMS (µrad)	P-V (µrad)	RMS (µm)	P-V (μm)	()	
0.85	3.77	0.03	0.05	7.7	2




Figure 2. Residual slope profile (red curve) and the corresponding residual height (blue curve). The mirror shows a radius of curvature of 7.7 km.